

External_Type	Material_Group	Substances	CAS_Number	Mass	Mass_Percentage_in_Leaf	Massmg
Wire	Pure metal	Aluminium (Al)	7429-90-5	0.10252	100.0	2.14708
			Subtotal	0.10252	100	2.14708
Die	Doped silicon	Silicon (Si)	7440-21-3	0.24828	100.0	5.2
			Subtotal	0.24828	100	5.2
Solder Wire	Tin alloy	Tin (Sn)	7440-31-5	0.02258	10.0	0.473
	Silver alloy	Silver (Ag)	7440-22-4	0.00452	2.0	0.0946
	Lead alloy	Lead (Pb)	7439-92-1	0.19874	88.0	4.1624
			Subtotal	0.22584	100	4.73
Wire	Pure metal	Aluminium (Al)	7429-90-5	0.06561	100.0	1.37413
			Subtotal	0.06561	100	1.37413
Lead Frame	Copper alloy	Phosphorous (P)	7723-14-0	0.00702	0.03	0.14694
	Pure metal layer	Zinc (Zn)	7440-66-6	0.00468	0.02	0.09796
	Pure metal layer	Tin (Sn)	7440-31-5	0.00702	0.03	0.14694
	Pure metal layer	Iron (Fe)	7439-89-6	0.02572	0.11	0.53877
	Pure metal layer	Copper (Cu)	7440-50-8	23.34117	99.81	488.8594
			Subtotal	23.38561	100	489.79001
Post-plating	Pure metal	Tin (Sn)	7440-31-5	0.2467	100.0	5.167
			Subtotal	0.2467	100	5.167
Mould Compound	Polymer	Tetrabromobisphenol A/Epichlorohydrin polymer	40039-93-8	2.27176	3.0	47.58
	Polymer	Phenol Formaldehyde resin (generic)	9003-35-4	4.54353	6.0	95.16
	Polymer	Epichlorohydrin/o-Cresol/Formaldehyde polymer (generic)	29690-82-2	7.57254	10.0	158.6
	Carbon Black	Carbon black	1333-86-4	0.37863	0.5	7.93
	Filler	Misc. Silica compounds (generic)	14808-60-7	59.06585	78.0	1237.08
	Flame retardant	Antimony Trioxide (Sb2O3) - cas no. 1309-64-4	1309-64-4	1.89314	2.5	39.65
			Subtotal	75.72545	100	1586
			Total	100.00001	100	2094.40822

Disclaimer

All information in this document is furnished for exploratory or indicative purposes only. All information in this document is believed to be accurate and reliable. However, WeEn Semiconductors does not give any representations or warranties as to the accuracy or completeness of such information and shall have no liability for the consequences of use of such information. WeEn Semiconductors may make changes to information published in this document at any time and without notice. Minor deviations may occur in the products from different manufacturing location. This document supersedes and replaces all information supplied prior to the publication hereof. Nothing in this document may be interpreted or construed as an offer to sell products that is open for acceptance or the grant, conveyance or implication of any license under any copyrights, patents or other industrial or intellectual property rights.