

External_Type	Material_Group	Substances	CAS_Number	Mass	Mass_Percentage_in_Leaf	Massmg
Die	Doped silicon	Silicon (Si)	7440-21-3	0.30848	100.0	6.6
			<b>Subtotal</b>	<b>0.30848</b>	<b>100</b>	<b>6.6</b>
Heat Spreader	Copper alloy	Phosphorous (P)	7723-14-0	0.01683	0.03	0.36
	Copper alloy	Iron (Fe)	7439-89-6	0.05609	0.1	1.2
	Copper alloy	Copper (Cu)	7440-50-8	56.01413	99.87	1,198.44
			<b>Subtotal</b>	<b>56.08705</b>	<b>100</b>	<b>NaN</b>
Post-plating	Pure Metal	Tin (Sn)	7440-31-5	1.26196	100.0	27
			<b>Subtotal</b>	<b>1.26196</b>	<b>100</b>	<b>27</b>
Lead Frame	Copper alloy	Phosphorous (P)	7723-14-0	0.00561	0.03	0.12
	Copper alloy	Iron (Fe)	7439-89-6	0.0187	0.1	0.4
	Copper alloy	Copper (Cu)	7440-50-8	18.67138	99.87	399.48
			<b>Subtotal</b>	<b>18.69569</b>	<b>100</b>	<b>400</b>
Die Attach	Lead alloy	Tin (Sn)	7440-31-5	0.05842	5.0	1.25
	Lead alloy	Silver (Ag)	7440-22-4	0.02921	2.5	0.625
	Lead alloy	Lead (Pb)	7439-92-1	1.08084	92.5	23.125
			<b>Subtotal</b>	<b>1.16847</b>	<b>100</b>	<b>25</b>
Isolator	Copper alloy	Phosphorous (P)	7723-14-0	0.00421	0.1	0.09
	Copper alloy	Aluminium Trioxide (Al2O3)	1344-28-1	3.85318	91.6	82.44
	Copper alloy	Nickel (Ni) - cas no. 7440-02-0	7440-02-0	0.03786	0.9	0.81
	Copper alloy	Molybdenum (Mo)	7439-98-7	0.29446	7.0	6.3
	Copper alloy	Manganese (Mn)	7439-96-5	0.01683	0.4	0.36
			<b>Subtotal</b>	<b>4.20654</b>	<b>100</b>	<b>90</b>
Mould Compound	Polymer	Phenol Formaldehyde resin (generic)	9003-35-4	0.26641	1.5	5.7
	Polymer	Epichlorohydrin/Diethyleneglycol Epoxy resin (generic)	25928-94-3	1.68729	9.5	36.1
	Filler	Silica fused	60676-86-0	15.62959	88.0	334.4
	Carbon Black	Carbon black	1333-86-4	0.17761	1.0	3.8
			<b>Subtotal</b>	<b>17.7609</b>	<b>100</b>	<b>380</b>
Wire	Pure metal	Aluminium (Al)	7429-90-5	0.29913	100.0	6.4
	Pure metal	Aluminium (Al)	7429-90-5	0.01784	100.0	0.3817
			<b>Subtotal</b>	<b>0.31697</b>	<b>200</b>	<b>6.7817</b>
Die Attach	Lead alloy	Tin (Sn)	7440-31-5	0.17457	90.0	3.735
	Lead alloy	Nickel (Ni) - cas no. 7440-02-0	7440-02-0	0.00097	0.5	0.02075
	Lead alloy	Silver (Ag)	7440-22-4	0.00485	2.5	0.10375
	Lead alloy	Antimony (Sb)	7440-36-0	0.01358	7.0	0.2905
			<b>Subtotal</b>	<b>0.19397</b>	<b>100</b>	<b>4.15</b>
			<b>Total</b>	<b>100.00003</b>	<b>100</b>	<b>NaN</b>

#### Disclaimer

All information in this document is furnished for exploratory or indicative purposes only. All information in this document is believed to be accurate and reliable. However, WeEn Semiconductors does not give any representations or warranties as to the accuracy or completeness of such information and shall have no liability for the consequences of use of such information. WeEn Semiconductors may make changes to information published in this document at any time and without notice. Minor deviations may occur in the products from different manufacturing location. This document supersedes and replaces all information supplied prior to the publication hereof. Nothing in this document may be interpreted or construed as an offer to sell products that is open for acceptance or the grant, conveyance or implication of any license under any copyrights, patents or other industrial or intellectual property rights.