

External_Type	Material_Group	Substances	CAS_Number	Mass	Mass_Percentage_in_Leaf	Massmg
Wire	Pure metal	Aluminium (Al)	7429-90-5	0.01286	100.0	0.26839
			Subtotal	0.01286	100	0.26839
Die	Doped silicon	Silicon (Si)	7440-21-3	0.11022	100.0	2.3
			Subtotal	0.11022	100	2.3
Solder Wire	Tin alloy	Tin (Sn)	7440-31-5	0.0101	10.0	0.21082
	Silver alloy	Silver (Ag)	7440-22-4	0.00202	2.0	0.04216
	Lead alloy	Lead (Pb)	7439-92-1	0.08891	88.0	1.85523
			Subtotal	0.10103	100	2.10821
Wire	Pure metal	Aluminium (Al)	7429-90-5	0.05145	100.0	1.07354
			Subtotal	0.05145	100	1.07354
Lead Frame	Copper alloy	Phosphorous (P)	7723-14-0	0.00704	0.03	0.14694
	Pure metal layer	Zinc (Zn)	7440-66-6	0.00469	0.02	0.09796
	Pure metal layer	Tin (Sn)	7440-31-5	0.00704	0.03	0.14694
	Pure metal layer	Iron (Fe)	7439-89-6	0.02582	0.11	0.53877
	Pure metal layer	Copper (Cu)	7440-50-8	23.42731	99.81	488.8594
			Subtotal	23.4719	100	489.79001
Post-plating	Pure metal	Tin (Sn)	7440-31-5	0.24762	100.0	5.167
			Subtotal	0.24762	100	5.167
Mould Compound	Polymer	Tetrabromobisphenol A/Epichlorohydrin polymer	40039-93-8	2.28015	3.0	47.58
	Polymer	Phenol Formaldehyde resin (generic)	9003-35-4	4.56029	6.0	95.16
	Polymer	Epichlorohydrin/o-Cresol/Formaldehyde polymer (generic)	29690-82-2	7.60049	10.0	158.6
	Carbon Black	Carbon black	1333-86-4	0.38002	0.5	7.93
	Filler	Misc. Silica compounds (generic)	14808-60-7	59.28383	78.0	1237.08
	Flame retardant	Antimony Trioxide (Sb2O3) - cas no. 1309-64-4	1309-64-4	1.90012	2.5	39.65
			Subtotal	76.0049	100	1586
			Total	99.99998	100	2086.70715

Disclaimer

All information in this document is furnished for exploratory or indicative purposes only. All information in this document is believed to be accurate and reliable. However, WeEn Semiconductors does not give any representations or warranties as to the accuracy or completeness of such information and shall have no liability for the consequences of use of such information. WeEn Semiconductors may make changes to information published in this document at any time and without notice. Minor deviations may occur in the products from different manufacturing location. This document supersedes and replaces all information supplied prior to the publication hereof. Nothing in this document may be interpreted or construed as an offer to sell products that is open for acceptance or the grant, conveyance or implication of any license under any copyrights, patents or other industrial or intellectual property rights.